

Foundations and Floor Slabs at Grade

Components

- Spread footings and wall footings
- Trenched footings/turned down footings
- · Drilled piers
- · Reinforced concrete foundation walls
- Reinforced concrete masonry walls utilizing normal weight masonry units with all cores grouted and reinforced
- Concrete grade beams
- Driven piles and pile caps
- · Auger cast piles and pile caps
- Other systems if recommended and acceptable to the geotechnical engineer and the structural engineer
- Where expansive clays are present on the site, the geotechnical investigation is to address such and special foundation and floor slab systems and/or undercutting and backfilling shall be utilized as recommended by the geotechnical engineering investigation.

Standards

- Foundations shall be designed by a structural engineer to meet the recommendations given by a geotechnical engineer based upon his geotechnical investigation and report and in accordance with the current state building code.
- 2. Structurally sound
- 3. Deflections and differential movement to be limited to magnitudes compatible with other building components
- 4. Compatible with soil type
- 5. Water Barrier
- 6. Long life expectancy
- 7. Do not use calcium chloride in concrete.
- 8. Sub-slab ventilation in areas with radon or potential soil gas submissions. Requirement for such is to be determined by qualified testing agency.
- Concrete minimum compressive strength at 28 days to be as required by structural engineer's design, but shall be no less than the following:
 - Foundations 3,000 psi
 - Floor slabs 3,000 psi
 - Precast systems 5,000 psi Strength of concrete provided is to be tested by independent testing lab, during construction
- 10. Concrete reinforcing steel shall be a minimum grade 60 and meet the requirements of the current state building code and structural engineer's design.
- 11. Project site concrete mixing shall not be used, unless otherwise approved by an independent testing agency.

Fly-Ash

Concrete materials may use 10%-20% fly-ash as replacement, but not addition. Mix design to be done by qualified independent testing agency.

Form Release

Use low- and non-toxic form releases.





- 12. For classrooms and corridor areas, use no less .than a 4" thick concrete slab with 6x6 W1.4 x W1.4 welded wire fabric.
- 13. Under concrete building slabs, place a minimum 10 mil vapor barrier and compact a minimum of 4" of drainage fill material unless geotechnical engineering investigation recommends otherwise.